


Always use correct Personal Protective Equipment


DUREPOX HARDENER

Description



A clear colourless Aliphatic Polyisocyanate resin solution used as the hardener component for Durepox Primer, Durepox HP Clear and DTM. This hardener is designed to reduce critical recoat time, increase dry time and improve chemical resistance.

Products




Product Type: Aliphatic Polyisocyanate Resin
Colour: Clear
Pot Life: N/A
Induction Time: N/A
Density: 01.051 kg/L
Recommended DFT: N/A
Theoretical Coverage: N/A

Properties



VOC: 340 g/L
Volume Solids: 66% (non catalysed)
Recoat-ability: N/A
Dry Time @ 20°C: N/A

Directions For Use



Mixing Ratio: 4:1 4 parts Durepox Primer
 (Volume) to 1 part Durepox Hardener

Thinning:

Note


Precautions: When opened the contents of Durepox Hardener should be used as soon as possible. The life of the content will be extended provided the screw cap is replaced firmly immediately after use. Excessive moisture contamination will cause the contents to foam and/or gel rendering Durepox Hardener unsuitable for use.

Health & Safety



For detailed information refer to Safety Data Sheet (SDS). Contains Isocyanates, avoid contact with skin and eyes.
 Avoid breathing vapour. Use protective clothing and respiratory equipment. Product is flammable.

Transport & Storage



Sizes: 250 ml, 1L, 4L
Class: 3A
Dangerous Goods: UN: 1263
Hazchem: 3[Y]
Packing Group: III
Shipment name: PAINT Related Material (Flammable)
Flash point: 27°C

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.