INFORMATION GUIDE



Factors Affecting Cathodic Protection

Salinity & Conductivity	The corrosion rate in seawater is up to 10 times faster than that in freshwater. Current requirements increase with salinity and thus seawater is low in resistivity.
Water Flow Rate	Freshwater is a less conductive electrolyte and is high in resistivity. It is a poor conductor and requires higher driving potentials. Magnesium anodes are widely used in freshwater applications.
Acidity	The increased velocity of water will increase the vessel's cathodic protection requirements. The water flow rate can be affected in high volume traffic areas (such as ports or busy recreational areas) and in high tidal areas.
Protective Coatings	The pH of water affects the rate of corrosion. With a decrease in pH levels there is an increase in the rate of corrosion.
Infrastructure	Protective coatings such as paints and propeller applications can improve the cathodic protection of a vessel. As protective coatings deteriorate there in an increase in the rate of corrosion for the exposed metal.
Proximity of Other Vessels	The proximity of other metals in the water affects the distance and often strength of ion flow between an anode and cathode. Consider a scenario of the relation between two vessels in a yacht club with neighbouring pens in contrast to the rate of corrosion between identical vessels on swing moorings 200m away.
Connection to Shore Power	When a vessel is connected to mains power it is also connected to that shore earth grounding system through the earth grounding on the shore power cable. The connection between vessels via the earth grounding conductor provides for galvanic corrosion between dissimilar metals on the vessels' connection.



This material remains the exclusive property of Marine Protection Systems Pty Ltd and must not be reproduced, replicated, copied or used without the expressed consent of Marine Protection Systems Pty Ltd © 2011

emarineprotectionsystems

(i) @marineprotectionsystems

Marineprosystems.com

CORROSION CONTROL THAT WORKS